

(19)



(11)

EP 2 888 246 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
13.12.2017 Bulletin 2017/50

(51) Int Cl.:
C07D 213/75 (2006.01) **C08F 222/14** (2006.01)
G01N 33/82 (2006.01)

(21) Application number: **13756924.0**

(86) International application number:
PCT/GB2013/052214

(22) Date of filing: **22.08.2013**

(87) International publication number:
WO 2014/030002 (27.02.2014 Gazette 2014/09)

(54) **MOLECULARLY IMPRINTED POLYMERS FOR THE CAPTURE OF BIOTIN**

MOLEKULAR GEPRÄGTE POLYMERE ZUR ANBINDUNG VON BIOTIN

POLYMÈRES À IMPRESSION MOLÉCULAIRE POUR CAPTURER LA BIOTINE

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

(30) Priority: **24.08.2012 GB 201215175**

(43) Date of publication of application:
01.07.2015 Bulletin 2015/27

(73) Proprietor: **The University of Kent Chatham Kent ME4 4TB (GB)**

(72) Inventor: **HALL, Andrew Chatham Maritime Chatham Kent ME4 4TB (GB)**

(74) Representative: **Boxall, Sarah Jane Boxall IPM Ltd 9 King Street Sandwich Kent CT13 9BT (GB)**

(56) References cited:

- **ELENA PILETSKA ET AL: "Biotin-specific synthetic receptors prepared using molecular imprinting", ANALYTICA CHIMICA ACTA, vol. 504, no. 1, 1 February 2004 (2004-02-01), pages 179-183, XP055088498, ISSN: 0003-2670, DOI: 10.1016/S0003-2670(03)00813-4 cited in the application**
- **JESPER WIKLANDER ET AL: "Towards a synthetic avidin mimic", ANALYTICAL AND BIOANALYTICAL CHEMISTRY, vol. 400, no. 5, 27 March 2011 (2011-03-27), pages 1397-1404, XP055088496, ISSN: 1618-2642, DOI: 10.1007/s00216-011-4907-5 cited in the application**
- **TOSHIFUMI TAKEUCHI ET AL: "Molecular Imprinting of Biotin Derivatives and Its Application to Competitive Binding Assay Using Nonisotopic Labeled Ligands", ANALYTICAL CHEMISTRY, vol. 72, no. 11, 1 June 2000 (2000-06-01), pages 2418-2422, XP055088497, ISSN: 0003-2700, DOI: 10.1021/ac991357s cited in the application**

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

EP 2 888 246 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to a polymerisable monomer and its use, after polymerisation, as a molecularly imprinted polymer for the capture of biotin, a biotin derivative, a biotin analogue or a biotinylated molecule.

5 **[0002]** In medical, food, environmental and chemical sciences, there is an increasing need for the selective separation of specific substances from complex mixtures of related substances. The end goal may be the preparative isolation of a certain compound or compounds, their analytical quantitation or the removal of impurities and/or unwanted side reagents from a reaction.

10 **[0003]** Current methods for selection, recognition and capture of compounds include the use of enzymes, antibodies, DNA and other biologically active compounds. While the use of biological capture molecules is preferred due to their high selectivity and affinity for their target, the use of such molecules is usually lengthy, expensive and often difficult to reproduce and repeat on a large scale. The use of synthetic alternatives has been investigated, an example of which is Molecularly Imprinted Polymers.

15 **[0004]** A Molecularly Imprinted Polymer (MIP) is a polymer that has been prepared using molecular imprinting which leaves cavities in a polymer matrix with affinity to a chosen "template" molecule. The process usually involves initiating the polymerisation of monomers in the presence of a template molecule that is extracted afterwards, thus leaving complementary cavities behind.

20 **[0005]** MIPs usually exhibit a high selectivity towards their substrate, analogous to antibody-antigen recognition (R. A. Bartsch, M. Maeda, Eds., *Molecular and Ionic Recognition with Imprinted Polymers* (Oxford University Press, Washington, 1998)) and sufficient affinity for the original, template molecule. A fast and cost-effective molecularly imprinted polymer technique has applications in many fields of chemistry, biology and engineering. Applications of MIPs are known, for example as affinity material for sensors, detection of chemical, antimicrobial and dye residues in food, adsorbents for solid phase extraction, binding assays, artificial antibodies, chromatographic stationary phase, catalysis, chemical separations, drug development and screening, and byproduct removal in chemical reaction. The technique has shown
25 promise in chiral separations of, for example, amino acid derivatives, peptides, phosphonates, aminoalcohols and beta-blocking compounds, affinity chromatography of nucleotides and the DNA-bases, as well as substitutes for antibodies in immunoassays for commercial drugs (Andersson et al (1995) *Proc. Natl. Acad. Sci.* 92: 4788-92). Generally, MIPs offer a number of advantages compared to natural receptors and antibodies. These include high mechanical, thermal and chemical stability, excellent operational and storage stability, simplicity of manufacturing and comparatively low price for material preparation.
30

[0006] Molecular imprinting is akin to making an artificial lock for a specific molecule that serves as a key. One of the greatest advantages of artificial receptors over naturally occurring ones is freedom of molecular design. The frameworks of artificial receptors are never restricted to proteins and a variety of skeletons (e.g., carbon chains and fused aromatic rings) can be used. Thus, the stability, flexibility, and other properties are freely modulated according to need. Even
35 functional groups that are not found in nature can be employed in these man-made compounds. Furthermore, when necessary, the activity to respond towards outer stimuli (photo-irradiation, pH change, electric or magnetic field, and others) can be provided by using appropriate functional groups. The spectrum of functions is far wider than that of naturally occurring receptors and capture molecules.

40 **[0007]** Molecular imprinting (MI) generally comprises the key steps shown in Figure 1. Monomers, termed functional monomers, are allowed to interact reversibly with a template molecule in solution. The template-monomer assemblies are copolymerized with a cross-linking monomer, resulting in a three-dimensional network polymer. The template is then displaced leaving an imprinted polymer that can be used for selective molecular recognition of the template compound or related substances.

45 **[0008]** MIPs of the correct size/shape may be packed in chromatographic columns and used for chromatographic separation of the template and related compounds from complex mixtures, on both analytical and preparative scales. Preparative applications can be separation of a compound from a complex mixture and isolation of the compound, e.g. through an affinity chromatography procedure where the strength of interactions with the stationary phase may be controlled through mobile phase modification. Further potential analytical applications are in competitive binding assays, chemical sensors or selective sample enrichments (Sellergren (1999) *Trends Anal. Chem.* 18: 164-174).

50 **[0009]** Non-covalent imprinting remains the most widely applied technique to generate molecularly imprinted binding sites (Sellergren et al (1988) *J. Am. Chem. Soc.* 110: 5853-60). This makes use of non-covalent self-assembly of the template with functional monomers prior to polymerisation, free radical polymerisation with a cross-linking monomer and then template extraction followed by rebinding by non-covalent interactions. This method is technically simple but relies on the success of stabilisation of the relatively weak interactions between the template and the functional monomers.
55 Stable monomer-template assemblies will, in turn, lead to higher concentrations of high affinity binding sites in the resulting polymer.

[0010] Materials for MIPs may be synthesised in any standard equipped laboratory in a relatively short time and some MIPs exhibit binding affinities and selectivities in an order of those exhibited by antibodies towards their antigens. Most

MIPs are synthesised by free radical polymerisation of functional monounsaturated (vinyl, acrylic, methacrylic) monomers and an excess of cross-linking di- or tri-unsaturated (vinyl, acrylic, methacrylic) monomers resulting in porous organic network materials. These polymerisations are relatively robust, allowing polymers to be prepared in high yield using different solvents (aqueous or organic) and at different temperatures. This is necessary in view of the varying solubilities of the template molecules.

[0011] The most successful non-covalent imprinting systems are based on commodity acrylic or methacrylic monomers, such as methacrylic acid (MAA), cross-linked with ethyleneglycol dimethacrylate (EDMA). Initially, derivatives of amino acid enantiomers were used as templates for the preparation of imprinted stationary phases for chiral separations (MICSPs), but this system has proven generally applicable to the imprinting of templates capable of engaging in hydrogen bonding or electrostatic interactions with MAA (Shea et al (1993) *J. Am. Chem. Soc.* 115: 3368-3369).

[0012] There are some classes of compound for which the generation of MIPs remains problematic, thus demanding the development of new functional monomers which are able to bind, preferably strongly, with such templates. One such example is biotin (vitamin H/B₇), which is necessary for cell growth, the production of fatty acids and the metabolism of fats and amino acids. Biotin is known to bind to the proteins streptavidin and avidin with one of the highest affinities known, with K_d ca. 10^{-14} to 10^{-15} M. The strength of this interaction is used extensively in biochemical assays. Here, biotin is conjugated to proteins, or other biomacromolecules. Because biotin is a small molecule (MW = 244.31), the biological activity of the biological molecule or biomacromolecule is generally unaffected. Any biotinylated biomacromolecule within the sample may then be extracted through incubation with (strept)avidin-modified stationary phases, while non-biotinylated molecules are simply washed away. The biotinylated molecules of interest may then be released through a thermal or chemical treatment of the stationary phase.

[0013] Although the avidin-biotin system is recognised as a useful tool for highly sensitive detection, it works only in aqueous solution. Therefore, the development of stable avidin-like materials with binding properties for biotin derivatives in organic solvents may enable the development of new avidin-biotin applications.

[0014] As with most biological-based systems, there are problems with the stability and storage of (strept)avidin-modified stationary phases and also limitations with the conditions under which they may be used. By contrast, MIPs are exceptionally robust materials, able to withstand extremes of pH and elevated temperature (to ca. 140 °C) and to be used in both aqueous and organic solvent environments. MIPs are also substantially cheaper to prepare than their biological counterparts. The ability to prepare a synthetic avidin via molecular imprinting will therefore lead a wide range of applications.

[0015] Previous attempts to create a MIP for the recognition of biotin have been reported, but have relied upon the use of excesses of commercially-available functional monomers, cocktails thereof chosen after computer modelling or from the use of a 2-amidopyridine monomer under poorly chosen conditions. For example, Wiklander et al (*Analytical and Bioanalytical Chemistry* (2011) 400(5): 1397-1404) prepared a MIP using a 4x excess of MAA as functional monomer, with respect to the template (biotin methyl ester), and found that polymerisation gave a polymer with a heterogeneous distribution of binding sites. The MIP showed a low population (7.7 $\mu\text{mol/g}$ polymer) of high affinity sites with $K_d = 4 \times 10^{-6}$ M and a far higher population (65 $\mu\text{mol/g}$ polymer) of lower affinity sites ($K_d = 1.6 \times 10^{-4}$ M). The binding here, measured in the non-competitive organic solvent chloroform, is at least eight orders of magnitude lower than for binding of biotin to streptavidin in water, while the heterogeneity of binding sites poses a further problem.

[0016] For example, in solid phase extraction, it is ideal if the solid phase extracts the target under one set of conditions (only) and releases all of the captured target under another set of conditions. Heterogeneous binding site distributions can mean that one or neither of these conditions is met. Also, the risk of non-specific binding to non-target species is increased if the binding site distribution is heterogeneous.

[0017] Takeuchi et al (*Anal. Chem.* (2000) 72: 2418-2422) compared the use of MAA as a functional monomer against 2-(trifluoromethyl)acrylic acid (TFAA), with EDMA as a cross-linker. The results show that MAA forms a MIP that binds biotin more effectively than a MIP generated from TFAA. While TFAA would be expected to be a more effective MIP because it is a stronger acid, the authors speculate that the lower binding affinity of the TFAA MIP is because TFAA is a good hydrogen bond donor but a weaker hydrogen bond acceptor. In contrast, MAA is a weaker acid and so acts as both a hydrogen bond donor and acceptor.

[0018] Piletska et al (*Anal Chim Acta* (2004) 504: 179-183) also investigated the use of MAA in a MIP for the capture of biotin. MAA as a monomer was compared with TFAA and 2-acrylamido-2-methylpropanesulphonic acid (AMPSA), using *N,N*-methylenebisacrylamide (MBAA) as a cross-linker. The resulting MIPs were photografted onto the surface of polystyrene microspheres with the aim of developing MIPs that are suitable for use in aqueous conditions. The best results were seen, again, with MAA but the results also showed that the MIPs functioned more effectively when supported on the microspheres suggesting that the MIP is highly flexible under aqueous conditions.

[0019] A recent paper by Ozcan et al (*J. Nanoparticle Res.* (2012) 14(6): 1-8) took a different approach to the design of a MIP for biotin. The resulting MIP was a semi-synthetic biotin-imprinted polymeric shell that is decorated on its surface with avidin cross-linked Au/Ag nanoclusters. The MIP showed a K_a of $3.89 \times 10^5 \text{M}^{-1}$ ($K_d = 2.57 \times 10^{-6}$ M or 2.57 μM) and was highly re-usable. The methodology described in the paper is a different type of imprinting, i.e. in inorganic polymers

(silica) rather than the organic polymers that are more robust, both in preparation and usage. While silica-based materials are more heat stable, they tend to be less pH stable.

[0020] Recently, a hierarchical molecular imprinting strategy has been described (Suriyanarayanan et al., (2013) Chem. Commun., 49: 5274-5276) wherein macroporous films with recognition sites selective for biotinylated compounds are prepared and their binding characteristics assessed via quartz crystal microbalance (QCM) measurements. These materials were prepared *via* the electro-polymerisation of commodity monomers - *p*-aminobenzoic acid and pyrrole - in the presence of biotin as template. The binding of only one biotin derivative (biotin methyl ester) is reported while the binding capacity of the imprinted films is not assessed.


Thus, there remains a need for a non-biological capture agent for biotin, biotin derivatives, biotin analogues and/or biotinylated molecules. The present invention seeks to overcome the problems of existing biotin-capturing MIPs by providing a novel functional monomer that recognises biotin, biotin derivatives, biotin analogues and/or biotinylated molecules. The monomer is suitable for polymerisation and the molecular imprinting of biotin, biotin derivatives, biotin analogues and/or biotinylated molecules to create an imprinted material that is selective for biotin, biotin derivatives, biotin analogues, relates substances and biotinylated biomacromolecules.

In particular, the invention encompasses a polymerisable monomer containing a recognition cleft for biotin, a biotin derivative, a biotin analogue or a biotinylated molecule comprising an isophthalic acid derivative or a pyridine-2,6-dicarboxylic acid derivative and a vinyl-2-aminopyridine derivative for use as part of a molecularly imprinted polymer.

[0021] Expressed in another way, the invention resides in a polymerisable monomer containing a recognition cleft for biotin, a biotin salt, a biotin ester, a biotin amide, a biotin carbonate, a biotin carbamate or a biotinylated molecule for use as part of a molecularly imprinted polymer, wherein the monomer is the compound of Formula (I) or Formula (II) as defined below. Previous attempts to create a biotin-selective MIP have used a monomer created from a single building block. In contrast, the functional monomer of the present invention is created from two different building blocks. In this way, the resulting monomer is shaped to contain a dipodal cleft formed by a diacid unit and two 2-aminopyridine units, at least one of which contains a vinyl group. As a result, the cleft is decorated with complementary hydrogen-bond sites that are spatially arranged within the cleft in a manner that allows for biotin binding. The monomer itself is not specific for biotin, biotin derivatives, biotin analogues or biotinylated molecules. Rather, the biotin specificity arises from the imprinting of the template-monomer complex. The use of the two building blocks also imparts structural rigidity to the monomer, thereby overcoming some of the drawbacks associated with the previously known monomers.

The monomers also possess at least one polymerisable function through at least one vinyl group. The monomer is used stoichiometrically with respect to the template (biotin, biotin derivative, biotin analogue or biotinylated molecule) species, i.e. in a 1:1 ratio, and so when polymerised, the resulting polymer provides a large population of uniform binding sites with high affinity for biotin, derivatives and analogues thereof and/or biotinylated molecules.


In one embodiment, the ratio of the isophthalic acid derivative to the vinyl-2-aminopyridine derivative is 1:2. Alternatively, the ratio of the isophthalic acid derivative to the vinyl-2-aminopyridine derivative is 1:1 and the monomer further includes a 2-aminopyridine unit. The monomer is the compound of Formula (I):



or the compound of Formula (II):

5

10




15

[0022] As will be seen from the structure of biotin below (Formula III), the cleft offered by the monomer provides a snug fit for biotin, a biotin derivative, a biotin analogue or a biotinylated molecule, which forms hydrogen bonds between the amido groups and the pyridine rings of the 2-aminopyridine derivatives on either side of the cleft.

20

25



30

(III)

35

[0023] The isophthalic acid derivative provides an exact width, or bridge, to the cleft, to space the 2-aminopyridine derivatives. The structure also provides the required rigidity to the monomer.

[0024] In both formulas, R^1 , R^2 , R^3 , R^4 and R^5 may be independently selected from the group consisting of H, alkyl with 1-10 carbon atoms, alkoxy with 1-10 carbon atoms, aryl with up to five substituents, amino, amido and halogen.

40

[0025] The R^1 group is preferably chosen to impart a desired solubility to the monomer. For example, R^1 may be a methyl, ethyl, propyl, tert-butyl, methoxy, ethoxy, propoxy, butoxy or benzyloxy group. A monomer wherein R^1 is *tert*-butyl has been found to be particularly suitable because of the ready commercial availability of 4-*tert*-butylisophthalic acid.

[0026] Groups R^2 to R^5 are selected both to assist in increasing monomer solubility and also to affect the basicity of the pyridine ring nitrogen. Groups R^2 - R^5 are preferentially hydrogen or methyl groups, due to the ready commercial availability of starting materials for preparation of these vinyl-2-aminopyridine building blocks.

45

[0027] In a further embodiment, the acid derivative is a substituted 2,6-pyridine dicarboxylic acid derivative. The pyridine group leads to increased rigidity of the cleft through hydrogen bonding, thereby increasing the biotin binding affinity of the monomers.

[0028] R^1 may be any alkyl group, such as methoxy, ethoxy, etc., but preferably, R^1 is 3-methylbutoxy.

[0029] Most preferably, the diacid derivative is 5-*t*-butylisophthaloyl dichloride. Ideally, the vinyl-2-aminopyridine derivative is 2-amino-5-vinylpyridine.

50

[0030] The monomer of the invention may be made by any suitable method. For example, the method comprises reacting two equivalents of a vinyl-2-aminopyridine derivative with one equivalent of an isophthalic acid derivative. In particular the method comprises:

55

- a) dissolving a diacid derivative in a solution using an appropriate anhydrous solvent, e.g. dichloromethane, chloroform or tetrahydrofuran;
- b) cooling the mixture to 0°C;
- c) adding a solution of vinyl-2-aminopyridine derivative and a tertiary amine;
- d) warming the mixture to room temperature and stirring for 24 hours; and

e) quenching the reaction by addition of water, separating the resulting organic and aqueous phases, washing and drying the organic phase, then evaporating the solvent to give the solid monomer.

In one embodiment, the ratio of the diacid derivative to the vinyl-2-aminopyridine derivative is 1:2. In another embodiment, the ratio of the diacid derivative to the vinyl-2-aminopyridine derivative is 1:1 and the method further comprises adding one equivalent of 2-aminopyridine before addition of one equivalent of a vinyl-2-aminopyridine derivative.

Isophthalic acid derivatives, vinyl-2-aminopyridine derivatives and 2-aminopyridine are commercially available or can be made by standard methods well known to the skilled person or methods analogous thereto, see for example Advanced Organic Chemistry by Jerry March, 4th Edition, John Wiley & Sons, 1992, Organic Syntheses, Volumes 1-8, John Wiley, edited by Jeremiah P. Freeman (ISBN: 0-471-31192-8), 1995, Fiesers' Reagents for Organic Synthesis, Volumes 1-17, John Wiley, edited by Mary Fieser (ISBN: 0-471-58283-2), and Handbook of Heterocyclic Chemistry, A. R. Katritzky et al, 3rd Edition, Elsevier, 2010.

The invention also encompasses a MIP obtained by polymerisation of at least one of the monomers described above with at least one cross-linking monomer in the presence of a template molecule, wherein the template molecule is selected from the group consisting of biotin, a biotin salt, ester, amide, carbonate, carbamate and a biotinylated molecule.

[0031] The cross-linker may be any suitable di-, tri- or tetra-vinyl monomer and will usually be selected according to the environment in which the polymer is to be used. For example, a polymer for use in organic media will require the use of a cross-linking monomer that has some hydrophobicity. Suitable cross-linking monomers in this instance include ethyleneglycol dimethacrylate, divinyl benzene and trimethylolpropane trimethacrylate. In contrast, a polymer that is to be used in an aqueous environment will require the use of a more hydrophilic cross-linking monomer. Suitable cross-linking monomers include bisacrylamides and pentaerythritol triacrylate.

The invention also relates to free-radical polymerisation of at least two of the monomers described above with at least one cross-linking monomer, in the presence of a template molecule, wherein the template molecule is selected from the group consisting of biotin, a biotin derivative and a biotinylated molecule.

Specifically the method comprises the steps of:

- i) formation of a template-functional monomer complex in a suitable solvent using non-covalent binding;
- ii) polymerisation with an excess of a cross-linking reagent initiated by a suitable polymerisation initiator; and
- iii) removal of the template to yield a complementary binding site for the template,

wherein the template is selected from the group consisting of biotin, a biotin derivative and a biotinylated molecule and the functional monomer is selected from the functional monomers described above.

The template may be biotin or a derivative thereof, such as an ester, amide, carbonate or carbamate.

Typical solvents used in the method include toluene, chloroform, acetonitrile, tetrahydrofuran and dimethylformamide.

Such solvents can also act as porogens, creating pores in the material which aid transport processes.

[0032] Any suitable polymerisation initiator may be used, for example azobisisobutyronitriles such as 2,2'-azobis(2,4-dimethyl valeronitrile) and 2,2'-azobis(4-methoxy-2,4-dimethyl valeronitrile).


After polymerisation, the template may be removed from the polymer by a washing procedure, such as a continuous extraction with methanol, dilute aqueous acid or another suitable solvent system capable of breaking the non-covalent bonds between the template and the polymeric binding site.

Still further, the invention relates to the use of a polymer as described above for the separation of the template molecule, related molecules and biotinylated macromolecules from complex mixtures. Immobilisation using the MIP of the present invention may be used to develop many applications with the addition of functionalities to the biotin-binding polymers, such as chiral stationary phase, sensing materials and specific adsorbents.

[0033] The invention will now be described in more detail by way of the following examples.

Example 1

[0034] The monomer of Formula I, where R¹, R², R³, R⁴ and R⁵ are all hydrogen, is synthesised in two steps by the reaction shown below:



[0035] Isophthaloyl dichloride (102 mg, 0.5 mmol) is dissolved in anhydrous dichloromethane (20 mL) and placed under a dinitrogen atmosphere. The solution is then cooled to 0°C using an ice bath. A solution of 2-aminopyridine (94 mg, 0.5 mmol) and triethylamine (51 mg, 0.5 mmol) in 10 mL dichloromethane is added dropwise to the cooled acid chloride solution. On completion of the addition, the ice bath is removed and the solution is allowed to stir at room temperature for 3 hours. At this point, the solution is cooled again to 0°C using an ice bath and a solution of 2-amino-5-vinylpyridine (60 mg, 0.5 mmol) and triethylamine (51 mg, 0.5 mmol) in 10 mL dichloromethane is added dropwise to the cooled solution. On completion of the addition, the ice bath is removed and the solution allowed to stir at room temperature overnight. The reaction is then quenched by the addition of 10 mL water. The organic and aqueous layers are separated, then the organic layer is washed with saturated aqueous sodium hydrogen carbonate solution (2 x 10 mL) and water (10 mL), before being dried over magnesium sulfate. After filtration, the solvent is evaporated under reduced pressure. The residue is then purified by column chromatography using silica gel as the stationary phase and ethyl acetate/hexanes as the mobile phase, to give the monomer, 1-N-(5-ethenylpyridin-2-yl)-3-N-(pyridin-2-yl)benzene-1,3-dicarboxamide, as a yellow solid.

Example 2

[0036] The monomer of formula II, where R¹, R², R³, R⁴ and R⁵ are all hydrogen, was synthesised through the reaction of two equivalents of 2-amino-5-vinylpyridine with one equivalent of isophthaloyl dichloride in the presence of triethylamine.

[0037] Thus, isophthaloyl dichloride (102 mg, 0.5 mmol) was dissolved in anhydrous dichloromethane (20 mL) and placed under a dinitrogen atmosphere. The solution was then cooled to 0°C using an ice bath. A solution of 2-amino-5-vinylpyridine (120 mg, 1 mmol) and triethylamine (101 mg, 1 mmol) in 10 mL dichloromethane was added dropwise to the cooled solution. On completion of the addition, the ice bath was removed and the solution allowed to stir at room temperature overnight. The reaction was then quenched by the addition of 10 mL water. The organic and aqueous layers were separated, then the organic layer was washed with saturated aqueous sodium hydrogen carbonate solution (2 x 10 mL) and water (10 mL), before being dried over magnesium sulfate. After filtration, the solvent was evaporated under reduced pressure. The residue was then purified by column chromatography, using silica gel as the stationary phase and ethyl acetate/hexanes as the mobile phase, to give the monomer, 1-N,3-N-bis(5-ethenylpyridin-2-yl)benzene-1,3-Dicarboxamide, as a yellow solid in 25% yield.

¹H NMR (CDCl₃, 400 MHz) δ: 8.33 (s, 2H), 8.12 (d, J = 2.2 Hz, 2H), 7.97 (dd, 7.8, 2.3 Hz, 2H), 7.92 (s, 1H), 7.66 (dd, J = 8.3, 2.3 Hz, 2H), 7.55 (t, J = 7.7 Hz, 1H), 6.94 (d, J = 8.3 Hz, 2H), 6.60 (dd, J = 17.6, 11.1 Hz, 2H), 5.77 (d, J = 17.6 Hz, 2H), 5.40 (d, J = 11.0 Hz, 2H)


Example 3

[0038] The monomer of Example 2 was studied for its ability to bind to a biotin derivative, the methyl ester of biotin, using a nuclear magnetic resonance titration method. The monomer of Example 2 bound the methyl ester of biotin with $K_a = 1220 \text{ M}^{-1}$ in deuterated chloroform. Such association constants are known to allow for the success of the stoichiometric imprinting protocols described further in this document.

Example 4

(comparative)

[0039] This monomer of formula IV, where R¹, R², R³, R⁴ and R⁵ are all hydrogen, was synthesised in two steps, as depicted below.



[0040] Pyridine-2,6-dicarbonyl dichloride (102 mg, 0.5 mmol) is dissolved in anhydrous dichloromethane (20 mL) and placed under a dinitrogen atmosphere. The solution is then cooled to 0°C using an ice bath. A solution of 2-aminopyridine

EP 2 888 246 B1

(94 mg, 0.5 mmol) and triethylamine (51 mg, 0.5 mmol) in 10 mL dichloromethane is added dropwise to the cooled acid chloride solution. On completion of the addition, the ice bath is removed and the solution is allowed to stir at room temperature for 3 hours. At this point, the solution is cooled again to 0°C using an ice bath and a solution of 2-amino-5-vinylpyridine (60 mg, 0.5 mmol) and triethylamine (51 mg, 0.5 mmol) in 10 mL dichloromethane is added dropwise to the cooled solution. On completion of the addition, the ice bath is removed and the solution allowed to stir at room temperature overnight. The reaction is then quenched by the addition of 10 mL water. The organic and aqueous layers are separated, then the organic layer is washed with saturated aqueous sodium hydrogen carbonate solution (2 x 10 mL) and water (10 mL), before being dried over magnesium sulfate. After filtration, the solvent is evaporated under reduced pressure. The residue is then purified by column chromatography using silica gel as the stationary phase and ethyl acetate/hexanes as the mobile phase, to give the monomer, 2-N-(5-ethenylpyridin-2-yl)-6-N-(pyridin-2-yl)pyridine-2,6-dicarboxamide, as a yellow solid.

Example 5

(comparative)

[0041] The monomer of formula V, where R¹, R², R³, R⁴ and R⁵ are all hydrogen, was synthesised through the reaction of two equivalents of 2-amino-5-vinylpyridine with one equivalent of pyridine-2,6-dicarbonyl dichloride (Sigma Aldrich) in the presence of triethylamine, as described for the preparation of the compound of formula II in Example 2.

[0042] Thus, pyridine-2,6-dicarbonyl chloride (102 mg, 0.5 mmol) is dissolved in anhydrous dichloromethane (20 mL) and placed under a dinitrogen atmosphere. The solution is then cooled to 0°C using an ice bath. A solution of 2-amino-5-vinylpyridine (120 mg, 1 mmol) and triethylamine (101 mg, 1 mmol) in 10 mL dichloromethane is added dropwise to the cooled solution. On completion of the addition, the ice bath is removed and the solution allowed to stir at room temperature overnight. The reaction is then quenched by the addition of 10 mL water. The organic and aqueous layers are separated, then the organic layer is washed with saturated aqueous sodium hydrogen carbonate solution (2 x 10 mL) and water (10 mL), before being dried over magnesium sulfate. After filtration, the solvent is evaporated under reduced pressure. The residue is then purified by column chromatography, using silica gel as the stationary phase and ethyl acetate/hexanes as the mobile phase, to give the monomer, 2-N,6-N-bis(5-ethenylpyridin-2-yl)pyridine-2,6-dicarboxamide, as a yellow solid.

Example 6

[0043] The polymer is synthesised by free radical polymerisation of a mixture of any one of the monomers prepared as described in Examples 1-4 and at least one cross-linking monomer, which may be ethyleneglycol dimethacrylate, trimethylolpropanetrimethacrylate, pentaerythritol triacrylate, a bis-acrylamide or divinylbenzene, in the presence of a solvent and a template and an initiator, which may be azobisisobutyronitrile. Further non-crosslinking monomers, that can be acrylamide, methacrylamde or 2-hydroxyethylmethacrylate, can also be added. The template can be biotin or a derivative thereof, such as an ester, amide, carbonate or carbamate. After polymerisation, the template is removed from the polymer by a washing procedure, which may be a continuous extraction with methanol.

[0044] Specifically, biotin methyl ester (258 mg, 1 mmol), the monomer of Example 2 (370 mg, 1 mmol) and ethyleneglycol dimethacrylate (3.96 g, 20 mmol) are dissolved in chloroform (5.6 mL) in a glass tube. Initiator (AIBN, 43.3 mg, 1% w/w total monomers) is added and the solution cooled on ice. Dinitrogen is sparged through the solution for ten minutes to remove dissolved oxygen and then the tube is sealed. The polymerisation is initiated by placing the sealed tube in a thermostat water bath set at 60°C) and the polymerisation is allowed to continue at this temperature for 24 hours. After this time, the tube is removed from the water bath and smashed to extract the monolithic polymer. The polymer is roughly broken into smaller pieces and then subjected to continuous extraction with methanol in a Soxhlet apparatus for 24 hours, to remove template and unreacted monomers. The extracted polymer is then further crushed and sized to yield particles of the desired size range, e.g. 25-36 microns for chromatographic use or 36-63 microns for use in solid phase extraction.

Example 7

[0045] The polymer prepared according to Example 6 is used for the selective separation of biotin, low molecular weight biotin derivatives and analogous compounds, and biotinylated biomacromolecules from complex mixtures. This can be done in chromatographic, batch or membrane modes.

[0046] For example, MIP particles (25-36 microns) are packed into a HPLC column, which is then attached to the HPLC, and used as the stationary phase in a liquid chromatographic separation. A sample containing a mixture, including a biotinylated species, is injected onto the column and flows through the column under the influence of the chosen mobile

phase. The transport of the biotinylated species along the length of the column under the influence of the mobile phase is preferentially retarded relative to non-biotinylated species due to specific interactions between the MIP stationary phase and the biotinylated species. Thus, the biotinylated species elutes from the column later and is effectively separated from other species present in the mixture.

5


Claims

1. A polymerisable monomer containing a recognition cleft for biotin, a biotin salt, a biotin ester, a biotin amide, a biotin carbonate, a biotin carbamate or a biotinylated molecule for use as part of a molecularly imprinted polymer, wherein the monomer is the compound of Formula (I):

10

15

20




25

Or the compound of Formula (II):

30

35



40

wherein R^1 , R^2 , R^3 , R^4 and R^5 are independently selected from the group consisting of: H, alkyl with 1-10 carbon atoms, alkoxy with 1-10 carbon atoms, aryl with up to five substituents, amino, amido and halogen.

45


2. A polymerisable monomer according to Claim 1, wherein R^1 is tert-butyl.
3. A polymerisable monomer according to Claim 1 or Claim 2, wherein R^2 , R^3 , R^4 and R^5 are H or methyl.
4. A molecularly imprinted polymer obtained by polymerisation of i) at least one of the monomers as claimed in any one of Claims 1 to 3 and ii) at least one cross-linking monomer, in the presence of a template molecule, wherein the template molecule is selected from the group consisting of biotin, a biotin salt, a biotin ester, a biotin amide, a biotin carbonate, a biotin carbamate and a biotinylated molecule.
5. A molecularly imprinted polymer according to Claim 4 wherein the cross-linking monomer is selected for use in organic media.
6. A molecularly imprinted polymer according to Claim 5, wherein the cross-linking monomer is a di-, tri- or tetra-vinyl monomer selected from the group comprising: ethyleneglycol dimethacrylate, divinyl benzene and trimethylolpropane trimethacrylate, bisacrylamides and pentaerythritol triacrylate.

55


7. A molecularly imprinted polymer according to Claim 4, wherein the cross-linking monomer is selected for use in aqueous media.
8. A molecularly imprinted polymer according to Claim 7, wherein the cross-linking monomer is selected from the group comprising: pentaerythritol triacrylate and bisacrylamides.
9. Use of a molecularly imprinted polymer as claimed in any one of Claims 4 to 8 to separate biotin, derivatives thereof and related compounds from a chemical or biological mixture.
10. Use of a molecularly imprinted polymer as claimed in any one of Claims 4 to 8 as a chemical sensor for the recognition of biotin, derivatives thereof and related compounds.

Patentansprüche

1. Polymerisierbares Monomer, eine Erkennungsspaltungsstelle für Biotin, ein Biotinsalz, einen Biotinester, ein Biotinamid, ein Biotincarbonat, ein Biotincarbamat oder ein biotinyliertes Molekül enthaltend, zur Verwendung als Teil eines molekular geprägten Polymers, wobei das Monomer die Verbindung der Formel (I):



oder die Verbindung der Formel (II):




ist, worin R¹, R², R³, R⁴ und R⁵ unabhängig ausgewählt sind aus der Gruppe bestehend aus: H, Alkyl mit 1-10 Kohlenstoffatomen, Alkoxy mit 1-10 Kohlenstoffatomen, Aryl mit bis zu fünf Substituenten, Amino, Amido und Halogenen.

2. Polymerisierbares Monomer nach Anspruch 1, wobei R¹ tert-Butyl ist.
3. Polymerisierbares Monomer nach Anspruch 1 oder Anspruch 2, wobei R², R³, R⁴ und R⁵ H oder Methyl sind.
4. Molekular geprägtes Polymer, erhalten durch eine Polymerisation von i) mindestens einem der Monomere nach einem der Ansprüche 1 bis 3 und ii) mindestens einem Vernetzungsmonomer in Anwesenheit eines Schablonenmoleküls, wobei das Schablonenmolekül ausgewählt ist aus der Gruppe bestehend aus Biotin, einem Biotinsalz, einem Biotinester, einem Biotinamid, einem Biotincarbonat, einem Biotincarbamat und einem biotinylierten Molekül.


5. Molekular geprägtes Polymer nach Anspruch 4, wobei das Vernetzungsmonomer zur Verwendung in einem organischen Medium ausgewählt ist.
6. Molekular geprägtes Polymer nach Anspruch 5, wobei das Vernetzungsmonomer ein Di-, Tri- oder Tetravinylmonomer ist, das ausgewählt ist aus der Gruppe bestehend aus: Ethylenglycoldimethacrylat, Divinylbenzol und Trimethyloxypropantrimethacrylat, Bisacrylamiden und Pentaerythritoltriacyrylat.
7. Molekular geprägtes Polymer nach Anspruch 4, wobei das Vernetzungsmonomer zur Verwendung in einem wässrigen Medium ausgewählt ist.
8. Molekular geprägtes Polymer nach Anspruch 7, wobei das Vernetzungsmonomer ausgewählt ist aus der Gruppe bestehend aus: Pentaerythritoltriacyrylat und Bisacrylamiden.
9. Verwendung eines molekular geprägten Polymers nach einem der Ansprüche 4 bis 8, um Biotin, Derivate desselben und verwandte Verbindungen aus einer chemischen oder biologischen Mischung abzutrennen.
10. Verwendung eines molekular geprägten Polymers nach einem der Ansprüche 4 bis 8 als chemischen Sensor für die Erkennung von Biotin, Derivaten desselben und verwandten Verbindungen.

Revendications

1. Monomère polymérisable contenant une clé de reconnaissance de la biotine, d'un sel de biotine, d'un ester de biotine, d'un amide de biotine, d'un carbonate de biotine, d'un carbamate de biotine ou d'une molécule biotinylée destiné à une utilisation comme partie d'un polymère imprimé par voie moléculaire, dans lequel le monomère est le composé de formule (I) :



ou le composé de formule (II) :



dans lesquelles R¹, R², R³, R⁴ et R⁵ sont choisis indépendamment dans le groupe constitué de : H, alkyle comportant 1 à 10 atomes de carbone, alcoxy comportant 1 à 10 atomes de carbone, aryle portant jusqu'à cinq substituants, amino, amido et halogène.

2. Monomère polymérisable selon la revendication 1, dans lequel R¹ est tert-butyle.
3. Monomère polymérisable selon la revendication 1 ou la revendication 1, dans lequel R², R³, R⁴ et R⁵ sont H ou méthyle.

EP 2 888 246 B1

- 5
4. Polymère imprimé par voie moléculaire obtenu par polymérisation i) de l'au moins des monomères revendiqués dans l'une quelconque des revendications 1 à 3 et i) d'au moins un monomère de réticulation, en présence d'une molécule gabarit, dans lequel la molécule gabarit est choisie dans le groupe constitué de la biotine, d'un sel de biotine, d'un ester de biotine, d'un amide de biotine, d'un carbonate de biotine, d'un carbamate de biotine et d'une molécule biotinylée.
- 10
5. Polymère imprimé par voie moléculaire selon la revendication 4, dans lequel le monomère de réticulation est choisi pour une utilisation dans des milieux organiques.
6. Polymère imprimé par voie moléculaire selon la revendication 5, dans lequel le monomère de réticulation est un monomère di-, tri- ou tétra-vinylé choisi dans le groupe comprenant : le diméthacrylate d'éthylène glycol, le divinylbenzène et le triméthacrylate de triméthylolpropane, les bisacrylamides et le triacrylate de pentaérythritol.
- 15
7. Polymère imprimé par voie moléculaire selon la revendication 4, dans lequel le monomère de réticulation est choisi pour une utilisation dans des milieux aqueux.
8. Polymère imprimé par voie moléculaire selon la revendication 7, dans lequel le monomère de réticulation est choisi dans le groupe comprenant : le triacrylate de pentaérythritol et les bisacrylamides.
- 20
9. Utilisation d'un polymère imprimé par voie moléculaire selon l'une quelconque des revendications 4 à 8 pour séparer la biotine, des dérivés de celle-ci et des composés apparentés d'un mélange chimique ou biologique.
- 25
10. Utilisation d'un polymère imprimé par voie moléculaire selon l'une quelconque des revendications 4 à 8 comme capteur chimique pour la reconnaissance de la biotine, de dérivés de celle-ci et de composés apparentés.

30

35


40

45

50

55

Figure 1



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Non-patent literature cited in the description

- Molecular and Ionic Recognition with Imprinted Polymers. Oxford University Press, 1998 [0005]
- **ANDERSSON et al.** *Proc. Natl. Acad. Sci.*, 1995, vol. 92, 4788-92 [0005]
- **SELLERGREN.** *Trends Anal. Chem.*, 1999, vol. 18, 164-174 [0008]
- **SELLERGREN et al.** *J. Am. Chem. Soc.*, 1988, vol. 110, 5853-60 [0009]
- **SHEA et al.** *J. Am. Chem. Soc.*, 1993, vol. 115, 3368-3369 [0011]
- **WIKLANDER et al.** *Analytical and Bioanalytical Chemistry*, 2011, vol. 400 (5), 1397-1404 [0015]
- **TAKEUCHI et al.** *Anal. Chem.*, 2000, vol. 72, 2418-2422 [0017]
- **PILETSKA et al.** *Anal Chim Acta*, 2004, vol. 504, 179-183 [0018]
- **OZCAN et al.** *J. Nanoparticle Res.*, 2012, vol. 14 (6), 1-8 [0019]
- **SURIYANARAYANAN et al.** *Chem. Commun.*, 2013, vol. 49, 5274-5276 [0020]
- **JERRY MARCH.** *Advanced Organic Chemistry.* John Wiley & Sons, 1992 [0030]
- *Organic Syntheses.* John Wiley, 1995, vol. 1-8 [0030]
- *Fiesers' Reagents for Organic Synthesis.* John Wiley, vol. 1-17 [0030]
- **A. R. KATRITZKY et al.** *Handbook of Heterocyclic Chemistry.* Elsevier, 2010 [0030]